

Cerakote® P-202 Arctic Black is designed to provide a thermal dissipating and electrically conductive finish for both metal and non-metal substrates. **Cerakote P-202 Arctic Black** is formulated to protect, lubricate and radiate heat. **Cerakote P-202 Arctic Black** is formulated to withstand high temperatures (500°F). **Cerakote P-Series** coatings maintain excellent adhesion even after repeated thermal cycling. These coatings provide maximum chemical and solvent resistance, and provide superior protection against high wear, galling and corrosion. In addition to performance, the **Cerakote P-Series** line of products is designed for ease of application. Each product is available in a single component, oven-cure system.

Cure Schedule:
350°F for 1 hour

Cerakote P-202 Arctic Black meets the requirements of MIL-L-46010E. Visit www.cerakote.com for more information.

Contact a Cerakote sales representative to determine which coating is appropriate for your application.

P-202 ARCTIC BLACK

Theoretical Solids by Weight	80% \pm 2%
Theoretical Coverage per gallon at 1.0 mil	1,284 ft ²
Viscosity	10 cP
Recommended Film Thickness	0.25 – 0.50 mil
5% Salt Spray (ASTM B117)	TBD
Pencil Hardness (ASTM D3363)	7H
Scratch Hardness (ASTM D3363)	6H
Adhesion Cross-Cut Tape (ASTM D3359)	5B
Mandrel Bend (ASTM D522)	100% Resistance
Impact (ASTM D2794)	160/160 inch-lbs
Density (g/mL)	0.83 g/mL
Strainer Size	325

*Results based on coated blasted steel cured at 350°F for 1 hour immediately after application.

Shelf Life: 12 Months from date of shipment

NIC Industries, Inc. does not warranty the use or application of the materials it manufactures or supplies. Our only obligation shall be to replace any defective materials supplied by us or refund the original purchase price of that product after we have determined the product to be defective. We assume no liability for damages of any kind and the user accepts the product "as is" and without any warranties, expressed or implied. The suitability of the product and/or intended use shall be solely the responsibility of the user.

All Cerakote coatings are VOC compliant under the EPA and have low to no VOC content. To find out the VOC content of an individual coating please contact sds@nicindustries.com for more information.

The information contained in this bulletin we believe to be correct to the best of our knowledge and testing. The recommendations and suggestions herein are made without guarantee or representation as to results. We recommend that you make adequate tests in your laboratory or plant to determine if this product meets all your requirements.

866-774-7628