

V-SERIES

***Preparation of substrate is crucial for maximum adhesion and performance of this material**

1. Remove all coatings, oils, and contaminants from substrate with either a degreasing chemical and/or by heating substrate to temperatures high enough to remove coatings or contaminants.
2. A blasted profile must be applied to the substrate to remove any rust, scale, or other coatings. This is required to ensure maximum adhesion. Remove any sharp edges or welding slag that may create thin areas or protrude through coating. For best results use a dry grit material such as aluminum oxide or garnet equivalent to a 100 - 120 mesh size. Glass beads are not recommended as they are not aggressive enough to produce a sufficient blast profile.
3. Place parts in an oven at 500°F for approximately 30 minutes to evaporate any last-minute moisture, oils, or contaminants that blasting or contact with skin have deposited on surface. Only **Cerakote®** approved solvents may be applied to substrate after completing the blast profile.
4. Hang parts to allow for best view and application access. This can be done by using support wires and hooks. Make sure to place parts in such a way that they will not bump into each other. Do not touch parts with bare skin.
5. Make sure the V-Series products are completely mixed and no solids remain in the bottom of the container. Failure to completely disperse the product will result in poor chemical ratios and product failure.
6. Blow off substrate with a high pressure air nozzle to remove any blasting dust left on the surface. Wear safety goggles of face shield for your protection. Work in a well ventilated area. If ventilation is not available, wear a respirator. See the SDS for additional information.
7. Recommended spray equipment is a high quality HVLP spray gun with a 0.8 mm tip, such as an IWATA LPH-80 (Cerakote Part #SE-138). Use a 100 mesh filter in the gun cup. The use of a small spray tip pattern will aid in coating hard to reach areas without excessive build up in surrounding areas. Electrostatic application may also be an option. Material does not need to be thinned. Use as received.
8. Two applications of product are recommended for a 1.0 to 2.0 mil film thickness. In some cases, a single coat will suffice for particular applications. Work from the most difficult surface out to the easiest. This will aid in reducing runs or excessive build up.
9. You may recoat parts prior to pre-bake or cure cycle if needed. Touch up cannot be performed after the cure cycle. If the parts need to be touched up after the cure cycle, the coating will need to be removed down to bare metal with the entire coating process repeated.
10. Allow to air-dry for 20 minutes, and then place in an oven at 175°F for 20 minutes to allow excess solvents from the coating to out-gas.
11. Ramp the oven up to 500°F. After desired temperature is reached, cure parts for 60 minutes. Higher cure temperatures are recommended for extreme application requirements. If parts are processed below 500°F, they have NOT fully cured. The final cure needs to take place at higher temperatures, which can occur with exhaust heat or the higher temperature cure cycles as mentioned above.
12. After cure cycle is complete, finished goods may be shipped once they have cooled to the touch.
13. Clean tools and equipment with acetone or **Cerakote** cleaning solvent.

*Please contact a **Cerakote** technician with questions on proper use and/or application. Onsite or offsite training courses are available for further instruction. **Consult your SDS for proper handling, disposal, cautions while using this product.***

NIC Industries, Inc. does not warranty the use or application of the materials it manufactures or supplies. Our only obligation shall be to replace any defective materials supplied by us or refund the original purchase price of that product after we have determined the product to be defective. We assume no liability for damages of any kind and the user accepts the product "as is" and without any warranties, expressed or implied. The suitability of the product and/or intended use shall be solely the responsibility of the user.

The information contained in this bulletin we believe to be correct to the best of our knowledge and testing. The recommendations and suggestions herein are made without guarantee or representation as to results. We recommend that you make adequate tests in your laboratory or plant to determine if this product meets all your requirements.